

194-NA25

Product Technical Information

Polypropylene - Homopolymer

194-NA25 is a high clarity injection moulding grade which can be used in many different applications. This grade contains an additive which could generate a slight almond odor in the finished articles. As such, for food contact applications we recommend you establish its suitability prior to use.

Applications

- Consumer products
- Transparent containers
- Medical syringes

Benefits and Features

- Good processability
- Good optical properties
- Good clarity
- Good rigidity and strength

Properties		Test Methods	Values	Units
Physical				
Melt Flow Rate	230°C/2.16kg	ISO 1133	25	g/10min
Mechanical				
Flexural Modulus	@23°C	ISO 178	1750	MPa
Tensile Strength	@Yield	ISO 527-1,-2	38	MPa
Izod impact strength, notched	@+23°C	ISO 180/1A	3	kJ/m ²
Charpy Impact Strength, notched	@+23°C	ISO 179/1eA	2	kJ/m ²
Thermal				
HDT	@0.45 MPa	ISO 75/B	116	°C
Optical				
Haze		ASTM D 1003	27	%

- Data should not be used for specification work

December, 2008

Published by
INEOS Olefins & Polymers Europe



194-NA25

Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, send an email to psnohreg@ineos.com.

Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Material Safety Data Sheet (MSDS) that may be obtained from the website www.ineospolyolefins.com. Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.

Exclusion of Liability

Although INEOS POLYOLEFINS endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS POLYOLEFINS is accurate and up to date, no representation or warranty, express or implied is made by INEOS POLYOLEFINS as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS POLYOLEFINS is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS POLYOLEFINS are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS POLYOLEFINS is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS POLYOLEFINS materials are suitable for the particular purpose intended and INEOS POLYOLEFINS shall not be responsible for any loss or damage caused by misuse of INEOS POLYOLEFINS products. To the maximum extent permitted by law, INEOS POLYOLEFINS accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS POLYOLEFINS materials or the use of INEOS POLYOLEFINS materials in conjunction with such other materials.