

# ExxonMobil™ PP9122

## Polypropylene Random Copolymer

### Product Description

A random copolymer resin designed for extrusion blow molding applications and thermoforming of medical and other specialty devices and packaging. It has excellent organoleptics and very low ash metal content.

### General

Availability <sup>1</sup>	▪ North America		
Features	▪ Autoclave Sterilizable ▪ Clean/High Purity	▪ Ethylene Oxide Sterilizable ▪ Low Extractables	▪ Low Odor ▪ Steam Sterilizable
Uses	▪ Caps ▪ Closures	▪ Labware ▪ Medical Packaging	▪ Medical/Healthcare Applications <sup>2</sup> ▪ Packaging
Appearance	▪ Natural Color		
Form(s)	▪ Pellets		
Processing Method	▪ Blow Molding ▪ Extrusion ▪ Extrusion Blow Molding	▪ Injection Blow Molding ▪ Profile Extrusion ▪ Sheet Extrusion	▪ Thermoforming
Revision Date	▪ 03/01/2010		

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.1 g/10 min	2.1 g/10 min	ASTM D1238
Density	0.900 g/cm <sup>3</sup>	0.900 g/cm <sup>3</sup>	ExxonMobil Method

Mechanical	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield 2.0 in/min (51 mm/min)	4140 psi	28.5 MPa	ASTM D638
Elongation at Yield (2.0 in/min (51 mm/min))	13 %	13 %	ASTM D638
Flexural Modulus - 1% Secant 0.051 in/min (1.3 mm/min)	141000 psi	972 MPa	ASTM D790A
0.51 in/min (13 mm/min)	166000 psi	1140 MPa	ASTM D790B

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Notched Izod Impact (73°F (23°C))	1.3 ft-lb/in	68 J/m	ASTM D256A

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Deflection Temperature Under Load (DTUL) at 66psi - Unannealed	179 °F	81.6 °C	ASTM D648

### Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

### Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

<sup>2</sup> This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use. For detailed Product Stewardship information, please contact Customer Service.